
**Paper, board and pulps — Measurement
of diffuse blue reflectance factor —**

**Part 1:
Indoor daylight conditions
(ISO brightness)**

*Papier, carton et pâtes — Mesurage du facteur de réflectance diffuse
dans le bleu —*

*Partie 1: Conditions d'éclairage intérieur de jour
(degré de blancheur ISO)*



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 2470-1:2009



COPYRIGHT PROTECTED DOCUMENT

© ISO 2009

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction.....	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle.....	2
5 Apparatus	2
5.1 Reflectometer.....	2
5.2 Reference standards for calibration of the instrument and the working standards	3
5.3 Working standards	3
6 Sampling and conditioning	3
7 Preparation of test pieces.....	3
8 Procedure	4
9 Expression of results	4
10 Precision.....	4
11 Test report.....	5
Annex A (normative) Spectral characteristics of instruments for measuring ISO brightness.....	6
Annex B (normative) UV calibration service.....	8
Bibliography.....	10

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 2470-1 was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*.

This first edition cancels and replaces ISO 2470:1999, which has been technically revised.

ISO 2470 consists of the following parts, under the general title *Paper, board and pulps — Measurement of diffuse blue reflectance factor*:

- *Part 1: Indoor daylight conditions (ISO brightness)*
- *Part 2: Outdoor daylight conditions (D65 brightness)*

Introduction

The reflectance factor (radiance factor) depends on the conditions of measurement, particularly the spectral and geometric characteristics of the instrument used. This part of ISO 2470 should therefore be read in conjunction with ISO 2469 which defines the geometric characteristics of the instrument and also defines the photometric calibration procedure to be adopted.

The definition of ISO brightness is historically linked to the Zeiss Elrepho instrument having, as a light source, an incandescent lamp which excites fluorescence to only a limited extent. It is specified here that, in instruments of the abridged spectrophotometer or filter colorimeter type, the UV content of the illumination be adjusted to conform to the CIE illuminant C as defined by a fluorescent reference standard having an assigned value of ISO brightness as described in Annex B. Only if this is done may the property measured on a fluorescent material be called ISO brightness.

STANDARDSISO.COM : Click to view the full PDF of ISO 2470-1:2009

STANDARDSISO.COM : Click to view the full PDF of ISO 2470-1:2009

Paper, board and pulps — Measurement of diffuse blue reflectance factor —

Part 1: Indoor daylight conditions (ISO brightness)

1 Scope

This part of ISO 2470 specifies a method for measuring the diffuse blue reflectance factor (ISO brightness) of pulps, papers and boards.

This part of ISO 2470 is limited in its scope to white and near-white pulps, papers and boards. The measurement can only be made in an instrument in which the ultraviolet energy level of the illumination has been adjusted to correspond to the CIE illuminant C using a fluorescent reference standard.

NOTE The property called D65 brightness is measured with an instrument adjusted to a much higher UV content than that specified in this part of ISO 2470. The measurement of D65 brightness is described in ISO 2470-2.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 186, *Paper and board — Sampling to determine average quality*

ISO 2469:2007, *Paper, board and pulps — Measurement of diffuse radiance factor*

ISO 3688, *Pulps — Preparation of laboratory sheets for the measurement of diffuse blue reflectance factor (ISO brightness)*

ISO 4094, *Paper, board and pulps — International calibration of testing apparatus — Nomination and acceptance of standardizing and authorized laboratories*

ISO 7213, *Pulps — Sampling for testing*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

radiance factor

β

ratio of the radiance of a surface element of a body in the direction delimited by a given cone with its apex at the surface element to that of the perfect reflecting diffuser under the same conditions of illumination

NOTE For fluorescent (luminescent) materials, the total radiance factor, β , is the sum of two portions, the reflected radiance factor, β_S , and the luminescent radiance factor, β_L , so that:

$$\beta = \beta_S + \beta_L$$

For non-fluorescent materials, the reflected radiance factor, β_S , is numerically equal to the reflectance factor R .

3.2

diffuse radiance [reflectance] factor

R

ratio of the radiation reflected and emitted from a body to that reflected from the perfect reflecting diffuser under the same conditions of diffuse illumination and normal detection

NOTE 1 The ratio is often expressed as a percentage.

NOTE 2 The diffuse radiance [reflectance] factor is influenced by the backing if the body is translucent.

NOTE 3 This part of ISO 2470 prescribes diffuse illumination and normal detection in an instrument calibrated in accordance with the provisions of this part of ISO 2470.

3.3

intrinsic radiance [reflectance] factor

R_{∞}

diffuse radiance [reflectance] factor of a layer or pad of material thick enough to be opaque, i.e. such that increasing the thickness of the pad by doubling the number of sheets results in no change in the measured radiance [reflectance] factor

NOTE The radiance [reflectance] factor of a single non-opaque sheet is dependent on the background and is not a material property.

3.4

ISO brightness

R_{457}

intrinsic radiance [reflectance] factor measured with a reflectometer having the characteristics described in ISO 2469, equipped with a filter or corresponding function having an effective wavelength of 457 nm and a half bandwidth of 44 nm, and adjusted so that the UV content of the irradiation incident upon the test piece corresponds to that of the CIE illuminant C

NOTE The filter function is described more fully by the weighting function factors given in Annex A and Table A.1.

4 Principle

A test piece is illuminated diffusely in a standard instrument and the light reflected normal to the surface is either allowed to pass through a defined optical filter and then measured by a photodetector or measured by an array of photosensitive diodes, where each diode responds to a different effective wavelength. The brightness is then determined directly from the output from the photodetector or by calculation from the photosensitive diode outputs using the appropriate weighting function.

5 Apparatus

5.1 Reflectometer

5.1.1 Reflectometer having the geometric, spectral and photometric characteristics described in ISO 2469 and calibrated in accordance with the provisions of ISO 2469, and equipped for the measurement of blue reflectance factor as defined in Annex A.

5.1.2 In the case of a filter reflectometer, the radiation falling upon the test piece shall have a UV content corresponding to that of the CIE illuminant C.

5.1.3 In the case of an abridged spectrophotometer, the instrument shall have an adjustable filter with a cut-off wavelength of 395 nm or some other system for adjustment and control, and this filter shall be adjusted or the system shall be calibrated with the help of the fluorescence reference standard (5.2.3), so that the UV content of the illumination falling upon the sample corresponds to that of the CIE illuminant C.

5.2 Reference standards for calibration of the instrument and the working standards

5.2.1 Use reference standards sufficiently frequently to ensure satisfactory calibration and UV adjustment.

NOTE This frequency interval can be fixed according to a defined schedule or control limits (e.g. from drift analysis of the measuring instrument).

5.2.2 Non-fluorescent reference standard for photometric calibration, issued by an ISO/TC 6 authorized laboratory in accordance with the provisions of ISO 2469.

5.2.3 Fluorescent reference standard for use in adjusting the UV content of the radiation incident upon the sample, having an ISO-brightness value assigned by an ISO/TC 6 authorized laboratory as prescribed in Annex B.

5.3 Working standards

5.3.1 Two plates of flat opal glass, ceramic or other suitable non-fluorescent material, cleaned and calibrated as described in ISO 2469.

NOTE In some instruments, the function of the primary working standard may be taken over by a built-in internal standard.

5.3.2 Stable plastic or other tablet, incorporating a fluorescent whitening agent.

5.3.3 Black cavity, having a reflectance factor which does not differ from its nominal value by more than 0,2 %, at all wavelengths. The black cavity should be stored upside down in a dust-free environment or with a protective cover.

NOTE The condition of the black cavity can be checked by reference to the instrument maker.

6 Sampling and conditioning

If the tests are being made to evaluate a lot of paper or board, the sample shall be selected in accordance with ISO 186. If a lot of pulps is to be evaluated, the sample shall be selected in accordance with ISO 7213. If the tests are made on another type of sample, make sure that the test pieces taken are representative of the sample received.

Conditioning according to ISO 187 is recommended but not required, but preconditioning with elevated temperatures should not be applied since it might change the optical properties.

7 Preparation of test pieces

Regarding pulp samples, prepare laboratory sheets in accordance with ISO 3688.

Avoiding watermarks, dirt and obvious defects, cut rectangular test pieces approximately 75 mm × 150 mm. Assemble at least ten of the test pieces in a pad with their top sides uppermost; the number should be such that doubling the number of test pieces does not alter the radiance factor. Protect the pad by placing an additional sheet on both the top and bottom of the pad; avoid contamination and unnecessary exposure to light or heat.

Mark the top test piece in one corner to identify the sample and its top side.

If the top side can be distinguished from the wire side, it shall be uppermost; if not, as may be the case for papers manufactured on double wire machines, ensure that the same side of the sheet is uppermost.

8 Procedure

8.1 Calibrate the instrument according to the instrument maker's instructions, using a non-fluorescent ISO level 3 reference standard (IR3) (5.2.2) or a working standard (5.3.1) calibrated in relation to an IR3. If the instrument is of the abridged spectrophotometer type, adjust the setting of the UV-adjustment filter or of a system having a corresponding function (see 5.1.3) using the fluorescent (5.2.3) and non-fluorescent (5.2.2) ISO level 3 standards, in accordance with the instrument maker's instructions.

8.2 Remove the protective sheets from the test piece pad. Without touching the test area, use the procedure appropriate to the instrument to measure the ISO brightness of the top side of the test piece pad. Read and record the value to the nearest 0,05 % or better, of the radiance factor.

8.3 Move the measured test piece to the bottom of the pad and determine the ISO brightness for the next test piece and similarly for the following test pieces until a total of not less than ten test pieces has been measured.

8.4 If required, turn the pad upside down and repeat the procedure for the other side.

NOTE 1 If, in the case of fluorescent samples, measurements are made with a filter with a cut-off wavelength of 420 nm placed in the light beam, it is possible to determine the ISO brightness of the non-fluorescent substrate and thus to calculate the contribution of the fluorescent whitening agent to the ISO brightness, but this is outside the scope of this part of ISO 2470.

NOTE 2 In the case of the non-fluorescent substrate or of a non-fluorescent material, the D65 brightness and the ISO brightness are identical.

9 Expression of results

Calculate the mean intrinsic radiance factor and its standard deviation for each required side, or the mean of the two sides, as the ISO brightness of the paper, board or pulp, in percent, to the nearest 0,5 % radiance factor. If the mean values differ by more than 0,5 % radiance factor and if this difference exceeds three times the standard deviation for the repeat measurements on a given side, the two sides shall be identified and the results reported separately. If the difference is equal to or less than 0,5 % radiance factor, the overall average shall be reported.

Although the measurements should be made to the nearest 0,05 % or better, radiance factor in accordance with the precision of the instrument, the final result should be expressed only to the nearest 0,5 % radiance factor as an indication of the lack of resolution in adjusting the UV filter.

10 Precision

The following data were obtained by the CEPI Comparative Testing Service, February 2007. The participating laboratories made ten measurements on each of the four samples. The means and standard deviations were then calculated as shown in Table 1.

Table 1 — Precision data

ISO brightness	Condition	Mean %	Within-laboratory standard deviation %	Reproducibility standard deviation %	Number of laboratories
UV adjusted	Non-fluorescent 1	80,36	0,26	0,33	20
	Non-fluorescent 2	90,63	0,06	0,33	18
	Fluorescent 1	86,24	0,17	0,30	20
	Fluorescent 2	99,52	0,09	0,43	19

11 Test report

The test report shall include the following information:

- a reference to this part of ISO 2470;
- date and place of testing;
- precise identification of the sample;
- whether the test pieces were conditioned and, if so, the conditioning atmosphere used;
- the mean ISO brightness and standard deviation for each required side, or the mean and standard deviation of the two sides, to the nearest 0,5 % radiance factor;
- the type of instrument used;
- any departure from this part of ISO 2470 or any circumstances or influences that may have affected the results.

Annex A (normative)

Spectral characteristics of instruments for measuring ISO brightness

A.1 Filter colorimeters

The effective wavelength of the reflectometer, $457,0 \text{ nm} \pm 0,5 \text{ nm}$, and the half-peak bandwidth of 44 nm are arrived at with a combination of lamps, integrating sphere, glass optics, filters and photoelectric detectors, taking into consideration that these parameters are dependent upon

- a) the relative spectral distribution of the radiant flux leaving the integrating sphere,
- b) the relative spectral transmittance of the glass optics,
- c) the relative spectral transmittance of the filters and spectral sensitivity of the detection system, and
- d) the relative spectral responsivity of the photoelectric detectors, each being a function of wavelength.

A.2 Abridged spectrophotometers

The $F(\lambda)$ of the brightness function at 5 nm intervals is indicated in Table A.1. In an abridged spectrophotometer measuring at 10 nm or 20 nm intervals, the appropriate values given in Table A.1 for the different wavelengths should be used in the calculation of ISO brightness without any attempt to recalculate intermediate values.

For the range of white and near-white papers for which this part of ISO 2470 is applicable, no further treatment of these functions is necessary.

Furthermore, in the case of a filter instrument, the area under the curve of $F(\lambda)$ for wavelengths exceeding 700 nm should be small enough for measurement not to be affected by any infrared fluorescent radiation generated in the sample.

Table A.1 — The relative spectral distribution function $F(\lambda)$ of a reflectometer equipped for measuring ISO brightness

Wavelength nm	$F(\lambda)$	5 nm weights	$F(\lambda)$	10 nm weights	$F(\lambda)$	20 nm weights
400	1,0	0,107	1,0	0,213	1,0	0,425
405	2,9	0,309				
410	6,7	0,715	6,7	1,430		
415	12,1	1,291				
420	18,2	1,942	18,2	3,885	18,2	7,728
425	25,8	2,752				
430	34,5	3,680	34,5	7,364		
435	44,9	4,790				
440	57,6	6,145	57,6	12,295	57,6	24,459
445	70,0	7,467				
450	82,5	8,801	82,5	17,609		
455	94,1	10,038				
460	100,0	10,668	100,0	21,345	100,0	42,463
465	99,3	10,593				
470	88,7	9,462	88,7	18,933		
475	72,5	7,734				
480	53,1	5,665	53,1	11,334	53,1	22,548
485	34,0	3,627				
490	20,3	2,166	20,3	4,333		
495	11,1	1,184				
500	5,6	0,597	5,6	1,195	5,6	2,378
505	2,2	0,235				
510	0,3	0,032	0,3	0,064		
Sum	937,4	100,000	468,5	100,000	235,5	100,000

Annex B (normative)

UV calibration service

B.1 General

In this part of ISO 2470, reference is made to special reference standards which are required to enable the relative UV content in the illumination falling on the test piece to be adjusted to conform to the CIE illuminant C.

To enable this to be done, the following procedure is established.

B.2 Standardizing laboratories

A laboratory, or laboratories, equipped to make primary spectrofluorimetric measurements using the two-monochromator method is appointed by ISO/TC 6 as "standardizing laboratory" in accordance with the provisions of ISO 4094. This laboratory issues "ISO reference standards of level 2" (IR2) to the authorized laboratories. Such reference standards shall be assigned spectral total radiance factor data for the CIE illuminant C.

B.3 Authorized laboratories

B.3.1 Laboratories having the necessary technical competence and maintaining reference instruments having the characteristics specified in ISO 2469 are appointed by ISO/TC 6 as "authorized laboratories" in accordance with the provisions of ISO 4094.

NOTE It is anticipated that these authorized laboratories will be the same as those authorized in accordance with the requirements of ISO 2469, but the standardizing laboratories will not necessarily be the same as those appointed according to ISO 2469 since different equipment is required.

B.3.2 The authorized laboratory shall make necessary adjustments to correct for differences in the basic photometric level between the instrument at the standardizing laboratory and the level specified for the authorized laboratory in ISO 2469, before calculating the ISO-brightness value of the IR2 and using this value to adjust the UV content of the reference instrument. The calculations shall be carried out using 10 nm data and the weighting functions given in Annex A.

B.3.3 The authorized laboratory shall, if necessary, take steps to ensure that directional effects in the IR2 which may affect the measurements at the standardizing laboratory are recognized and taken into account when determining the value to be used when transferring this calibration to an instrument providing a diffuse illumination.

B.4 IR3 fluorescent reference standard

B.4.1 The fluorescent reference standard shall consist of white paper, uniform in radiance factor and aged for a sufficient time to give the paper an optical stability of 4 to 6 months without a deterioration in the ISO-brightness value of more than 0,1 %.

B.4.2 The standard shall be prepared in the form of opaque pads and shall have a smooth non-glossy surface. The pad shall be covered with a suitable protective cover.