

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space®
INTERNATIONAL

400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION

SAE

AMS 3217/1A

Issued 1 JUL 1983

Revised 1 APR 1993

Superseding AMS 3217/1

Submitted for recognition as an American National Standard

TEST SLABS, ACRYLONITRILE BUTADIENE (NBR-H) Medium-High Acrylonitrile, 65 - 75

1. SCOPE:

1.1 Form:

This specification covers a standard acrylonitrile butadiene (NBR-H) rubber stock with medium-high acrylonitrile content in the form of molded test slabs.

1.2 Application:

See AMS 3217.

2. APPLICABLE DOCUMENTS:

See AMS 3217.

3. TECHNICAL REQUIREMENTS:

3.1 Basic Specifications:

The complete requirements for test slabs described herein and their procurement shall consist of this document and the latest issue of the basic specification AMS 3217.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

AMS 3217/1A

SAE

AMS 3217/1A

3.2 Material:

(R)

Shall be a high-acrylonitrile butadiene (NBR-H) compounded to the formulation shown in Table 1.

Table 1 - Formulation

Ingredients	NIST SRM Number	Parts
Hycar 1002® or equivalent*	-	100.0 (See 3.2.1)
Zinc Oxide	370	5.0 (See 3.2.2)
Stearic Acid	372	1.5 (See 3.2.2)
Sulfur	371	1.5 (See 3.2.2)
Philblack A®, N550 or equivalent* (See 3.2.3)	-	45.0 (See 3.2.1)
Altax® or equivalent*	-	1.5 (See 3.2.2)

Press Cure: 20 minutes $\pm$ 0.5 at
155 °C $\pm$ 3 (311 °F $\pm$ 5).

*Equivalent ingredients must be approved by Wright Laboratory (WL/MLSE),
WPAFB, OH 45433-6533.

3.2.1 Weigh parts to the nearest 0.1 gram.

3.2.2 Weigh parts to the nearest 0.02 gram.

3.2.3 ASTM D 1765 designation.

3.3 Processing:

After the elastomer has banded on the rubber mill, the other ingredients shall be added in the order listed in Table 1.

3.3.1 The stock shall not be allowed to become hotter than can be handled with the bare hands; it is recommended that the stock be removed from the mill and cooled to room temperature before incorporating the final ingredient.

3.3.2 After all ingredients have been incorporated and the stock has been thoroughly milled, the stock shall be passed 10 times through a tight mill.

3.3.3 Suitable preforms shall be cut from the freshly milled stock and molded into test slabs as specified in ASTM D 3182, Figure 1.