



AEROSPACE MATERIAL SPECIFICATION

AMS4069™**REV. F**

Issued 1959-06
Reaffirmed 2006-04
Revised 2015-12

Superseding AMS4069E

Aluminum Alloy, Drawn, Round Seamless Tubing
Close Tolerance
2.5Mg - 0.25Cr (5052-O)
Annealed
(Composition similar to UNS A95052)

RATIONALE

AMS4069F revises Properties (3.3.1.1) and Reports (4.4.1), and is a Five Year Review and update of this specification.

1. SCOPE

1.1 Form

This specification covers an aluminum alloy in the form of drawn, round seamless tubing 0.010 to 0.450 inch (0.25 to 11.43 mm), inclusive, in wall thickness (see 8.4).

1.2 Application

This tubing has been used typically for ducts requiring small radius bends, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

AMS2355 Quality Assurance, Sampling and Testing, Aluminum Alloys and Magnesium Alloy, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2015 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS4069F>**

SAE WEB ADDRESS:

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM B660 Packaging/Packing of Aluminum and Magnesium Products

ASTM B666/B666M Identification Marking of Aluminum and Magnesium Products

2.3 ANSI Accredited Publications

Copies of these documents are available online at <http://webstore.ansi.org/>.

ANSI H35.2 Dimensional Tolerances for Aluminum Mill Products

ANSI H35.2M Dimensional Tolerances for Aluminum Mill Products (Metric)

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight as shown in Table 1, determined in accordance with AMS2355.

Table 1 - Composition

Element	min	max
Silicon	--	0.25
Iron	--	0.40
Copper	--	0.10
Manganese	--	0.10
Magnesium	2.2	2.8
Chromium	0.15	0.35
Zinc	--	0.10
Other Elements, each	--	0.05
Other Elements, total	--	0.15
Aluminum	remainder	

3.2 Condition

Annealed.

3.3 Properties

Tubing shall conform to the following requirements, determined on the mill product in accordance with AMS2355:

3.3.1 Tensile Properties

Shall be as shown in Table 2 for tubing 0.010 to 0.450 inch (0.25 to 11.43 mm), inclusive, in specified wall thickness.

- 3.3.1.1 Mechanical property requirements for product outside the range covered by 1.1 shall be agreed upon between purchaser and producer.

Table 2 - Tensile properties

Property	Value
Tensile Strength	25.0 to 35.0 ksi (172 to 241 MPa)
Yield Strength at 0.2% Offset	10.0 to 20.0 ksi (68.9 to 138 MPa)
Elongation in 2 inches (50.8 mm), min	
Strip	10%
Full Section	12%

3.3.2 Flattening

Tubing having nominal wall thickness less than 10% of the nominal OD shall withstand, without cracking, flattening sideways under a load applied gradually at room temperature until the outside dimension under load is equal to three times the nominal wall thickness.

- 3.3.2.1 If tubing does not pass the flattening test of 3.3.2, a section of tube not less than 1/2 inch (12.7 mm) in length and embracing one-third to one-half the circumference of the tube shall withstand, without cracking, bending at room temperature through an angle of 180 degrees around a diameter equal to the nominal wall thickness of the tubing with axis of bend parallel to axis of tube and with inside of tube on inside of bend.

3.4 Quality

Tubing, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the tubing.

3.5 Tolerances

Except as specified in 3.5.1 for mean diameter, tolerances shall conform to all applicable requirements of ANSI H35.2 or ANSI H35.2M.

3.5.1 Mean Diameter

Shall be as shown in Table 3. Mean diameter is the average of two measurements taken at right angles to each other at the same longitudinal location on the tube.

Table 3A - Mean diameter, inch/pound units

Nominal OD Inches		Tolerance Inch Plus and Minus
0.500 to	1.000, incl	0.002
Over 1.000 to	3.000, incl	0.003
Over 3.000 to	5.000, incl	0.004
Over 5.000 to	6.000, incl	0.005
Over 6.000 to	8.000, incl	0.008
Over 8.000 to	10.000, incl	0.010
Over 10.000 to	12.000, incl	0.013

Table 3B - Mean diameter, SI units

Nominal OD Millimeters		Tolerance Millimeter Plus and Minus
	12.70 to 25.40, incl	0.05
Over	25.40 to 76.20, incl	0.08
Over	76.20 to 127.00, incl	0.10
Over	127.00 to 152.40, incl	0.13
Over	152.40 to 203.20, incl	0.20
Over	203.20 to 254.00, incl	0.25
Over	254.00 to 304.80, incl	0.33

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The producer of tubing shall supply all samples for producer's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the tubing conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Composition (3.1), tensile properties (3.3.1), and tolerances (3.5) are acceptance tests and, except for composition, shall be performed on each inspection lot.

4.2.2 Periodic Tests

Flattening (3.3.2) is a periodic test and shall be performed at a frequency selected by the producer unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing

Shall be in accordance with AMS2355.

4.4 Reports

The producer of tubing shall furnish with each shipment a report stating that the product conforms to the chemical composition and tolerances, and showing the numerical results of tests on each inspection lot to determine conformance to the other acceptance test requirements. This report shall include the purchase order number, inspection lot number(s), AMS4069F, size, and quantity. The report shall also identify the producer, the product form, and the size of the mill product.

4.4.1 When the product size is outside the range covered by 1.1, the report shall contain a statement to that effect.

4.5 Resampling and Retesting

Shall be in accordance with AMS2355.